# **Product Information**

**MOVING YOUR WORLD** 



## **ANTICORIT 988**

### A lubricant, dewatering fluid, penetrating oil and a rust inhibitor in one

#### **Description**

ANTICORIT 988 has a variety of uses industrially, as a rust inhibitor it is superb and, after one application, rusting and scaling can be removed with a wire brush. Where there is particularly heavy or stubborn rusting, a second application may be necessary to help remove the corrosion and leave the metal surface fully protected with a micro-thin oily film. After use ANTICORIT 988 may be removed using a solvent, hot detergent wash or by wiping.

#### **Application**

ANTICORIT 988 is an oil based product which also contains solvent that allows rapid penetration to inaccessible areas. The solvent evaporates leaving an oily film which lubricates the components enabling the immovable parts to be manipulated.

Use as a penetrating and release agent when heavy duty threaded fastenings become seized either due to the effects of corrosion or heat.

ANTICORIT 988 is particularly suitable for corrosion protection on the following types of components:-

- Small Individual ferrous and non-ferrous items.
- · Assembled parts ferrous and non-ferrous.
- · Complex assemblies with internal surfaces.
- Large simple assembled items.
- · Delicate mechanisms

#### Advantages/Benefits

- · Excellent dewatering properties
- Solvent deposited
- Lubricates and penetrates
- · Provides an ultra thin anti-corrosion protective film
- Medium drying properties
- After drying, treated items are not slippery or difficult to handle

#### **Specifications**

• BS1133 Classification TP 2b

#### Cleaning

Fuchs recommends the use of our fully compatible RENOCLEAN cleaners to clean your components. Please refer to data sheets, or contact your local Fuchs Area Manager to discuss your requirements.

#### **Method of Application**

ANTICORIT 988 may be applied by spraying, dipping or brushing.

Available in Aerosol as FUCHS MAINTENANCE SPRAY.

PM3-UK IND 1016935 Feb 24 Page 1 of 3















# **Product Information**

**MOVING YOUR WORLD** 



#### **CHARACTERISTICS: ANTICORIT 988**

Characteristics	Unit	Value	Test Method
Appearance		Hazy brown mobile fluid	
Specific gravity at 15.6°C		0.805	IP160
Flash point (PMCC)	°C	40	IP34
Water displacing properties IP178 Method B (Mod.)	%	90 min.	
Film forming content	%wt	20	
Corrosion test Salt spray	(hours free of corrosion)	92	ASTM B117
Corrosion test Humidity cabinet	(hours free of corrosion)	500	BS1133
Classification		TP 2b	BS1133
Approx. wet coverage to give a dry film thickness of 0.025 mm:	m²/litre	8	
Drying time (approx.)	hours	1 to 2	

#### **Protection Term**

Indoors months

2 (covered) Outdoors months

#### **NOTE**

The performance of this product may be compromised should it be stored for long periods in open containers

PM3-UK IND 1016935 Feb 24 Page 2 of 3











## **Product Information**

**MOVING YOUR WORLD** 



#### **Notes**

The information contained in this product information is based on the experience and know-how of FUCHS LUBRICANTS (UK) plc in the development and manufacturing of lubricants and represents the current state-of-the-art. The performance of our products can be influenced by a series of factors, especially the specific use, the method of application, the operational environment, component pre-treatment, possible external contamination, etc. For this reason, universally valid statements about the function of our products are not possible.

Our products must not be used in aircraft or spacecraft. Our products may be used in manufacture of components for aircraft or spacecraft if they are removed without residue from the components prior to assembly into the aircraft or spacecraft.

The information given in this product information represents general, non-binding guidelines. No warranty expressed or implied is given concerning the properties of the product or its suitability for any given application. We therefore ommend that you consult a FUCHS LUBRICANTS (UK) plc application engineer to discuss application conditions and the performance criteria of the products before the product is used. It is the responsibility of the user to test the functional suitability of the product and to use it with the corresponding care.

Our products undergo continuous improvement. We therefore retain the right to change our product program, the products, and their manufacturing processes as well as all details of our product information sheets at any time and without warning, unless otherwise provided in customer-specific agreements. With the publication of this product formation, all previous editions cease to be valid. Any form of reproduction requires express prior written permission from FUCHS LUBRICANTS (UK) plc.

© FUCHS LUBRICANTS (UK) plc. All Rights reserved.













